

AMENDMENTS TO THE SPECIFICATION

Please amend the paragraph beginning at pg. 14, line 8 as follows:

Moreover, it is quite effective to arrange a metal foil serving as a junction auxiliary material (brazing material) on a barrier surface between both metals. In this case, the foil thickness is normally 0.1 mm or below but not limited to a specific thickness. Thus, it is possible for the different metals to become unified metallurgically in ~~the different metals to be~~ a unified block, thereby significantly increasing the superconducting characteristic and workability.